



VITCON 2009 RAINKOTE **(POLYMER COATING)**

Impregnated Coating

DESCRIPTION

VITCON 2009 RAINKOTE is a polymer based liquid. On application with simple brush or spray **VITCON 2009 RAINKOTE** forms a thin elastomeric film covering all hidden cracks and porosity and shielding the wall from penetrating of water for several years. is unaffected by U.V. radiation ensuring longer life. Though the film formed by this material is vapour permeable, but no water can penetrate through the film - essential requirement of any exterior coating. The film keeps fungi & algae away for few years. **VITCON 2009 RAINKOTE** has a very good penetrating ability.

APPLICATION

Remove all loose particles, dust, growing moss and debris from the surface. Wet the surface by spraying water & dry it. Coat the material either by spray or brush. Dipping process is ideal for impregnating bricks, roofing tiles. After coating or dipping a minimum 6-8 hour drying time is required. Within this period no water should come in contact with coated surface. To ensure better water proofing, 24 hours drying time is recommended.

SPECIFICATIONS

Appearance	: Colourless liquid
Sp. Gravity	: 1.01 ± 0.02
pH Value	: 8 - 9
Chloride content	: Nil
Shelf life	: 12 months
Storage	: Under shade



COVERAGE

- ✓ Plastered surface : 18 - 20 square meter per liter
- ✓ Strongly absorbent bricks : 8 - 10 square meter per liter
- ✓ Concrete surface : 45 – 50 square meter per liter

PACKAGING

VITCON 2009 RAINKOTE is available in 35kg, 50kg and 240kg HDPE drums.

SAFETY

VITCON 2009 RAINKOTE is non-toxic, non-flammable and non hazardous. However, any splash on the human body should be washed out immediately with plenty of water. Local exhaust is recommended for enclosed area.